



HAYCARB
Activated carbon solutions

Haycarb Gold Series

CIC/CIP/CIL Gold Extraction

RPMC 1003 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 55	ASTM
Iodine Number (mg/g)	Min: 1100	ASTM
Apparent Density (g/cc)	Min: 0.48	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness No.	Min: 99	ASTM
Particles size 6x12 US mesh		ASTM
> 6 mesh (3.35 mm) (% by wt)	Max: 5	ASTM
6x12 (3.35 mm x 1.70 mm) (% by wt)	Min: 90	ASTM
< 12 mesh (1.70 mm) (% by wt)	Max: 5	ASTM



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com